



Sun Ray Electric Material Co., Ltd

Product Specification Sheet

Anti-Static Epoxy Glass Fiber Laminate

Thickness : 0.2~72 (mm)

Dimension : 920 * 1220、1020 * 1220、1060 * 1220 (mm)

Color : Black

Product Code 型號		SR1400AK	SR380
Surface Resistance 表面電阻 (ESD)	Ω	$10^5 \sim 10^9$	$10^5 \sim 10^9$
Flexural Strength 彎繞強度	kg/mm ²	35~45	35~45
Compressive Strength 壓縮強度	kg/mm ²	20~40	20~40
Impact Strength 衝擊強度 Lengthwise 經向 Crosswise 緯向	kg-cm/cm ²	68~78 35~45	68~78 35~45
Specific Gravity 比重	-	1.9	1.9
Glass Transition Temperature 玻璃轉化溫度	°C	125~130	-
吸水率 Water Absorption	%	<0.2	<0.2
Heat Resistance 耐熱性 (Use the thickness of 5mm un-machining raw material testing. 使用厚度 5mm 未加工材料測試)	180°C	180 min	-
	280°C	-	>90 min
	288°C	-	>60 min
	300°C	-	>30 min
Flame Resistance 耐燃性	-	HB	